

SPECIFICATIONS

PROPERTIES	SPECIFICATIONS
Acid number, mg KOH/g	15 Maximum
Softening Point (R & B), °C	96 – 105
Color (50% in Toluene), Gardner	5 Maximum
Appearance	Amber colored crystalline solid

FEATURES

Soluble in aromatic and aliphatic hydrocarbon solvents, soluble in esters and ketones, insoluble in methanol, ethanol, isopropanol and water.

Compatible with EVA (Ethylene and Vinyl-Acetate Copolymer), natural and synthetic rubbers and other polymers.

APPLICATIONS

AMBERYL 1200 is recommended for use in Hot Melts adhesive formulations, contact adhesives, coatings and other applications.

STABILITY AND STORAGE

Handle with caution avoiding any spillage. Keep the bags closed. Store indoors without direct sunlight in a cool place free from moisture so that the product maintains its properties. Resin flakes and pastilles tend to have oxidations, which could cause darkening colour and can also affect on solubility with extend storage and/or exposed to heat

PACKAGING

Bags 25 kg
